

PRZEDSIĘBIORSTWO USŁUGOWO REMONTOWE
REMODEX
ZAKŁAD BADAŃ I WDROŻEŃ PRZEMYSŁU MEBLARSKIEGO
Spółka z o.o.

Gruszczyn, ul. Leśna 12
62-006 Kobylnica

e-mail: biuro@remodex.com.pl
KRS 0000099068

tel./fax. 61 817-49-97
tel. kom. 601 391 825

SIGN: BW/JK/128/19

DATE: 2019-09-11

Order from: 2019-07-29

TEST REPORT

Determination of the abrasion resistance of fabric by Martindale method


1. *Name and type of article* - **Fabric LS-8**
2. *CLIENT* - P.H. „STEMA” Stefan Boczyło
ul. Towarowa 22A
58-100 ŚWIDNICA
3. *Type of test*
- **resistance to abrasion by Martindale method**
 - inspection intervals after 1000, 2000, 5000 and 10000 cycles
 - the number cycles: average – **90.000**
 - after 100 000 cycles in all abrasion tests at the edges of the fabric.
 - **resistance to pilling**
(modified Martindale’s method)
 - loading – 260 g.
 - translational movement along Lissajous tracks
 - after 2000 cycles – degree of change **5 (no changes)**
 - after 5000 cycles – degree of change **5 (no changes)**
4. *Documents identifying article* - order.
- This article was tested in accordance with the test procedures described in:
- PN-EN ISO 12947-2:2017**
PN-EN ISO 12945-2:2002
for conformity with PN-EN 14465:2005/A1:2007, annex A

TEST RESULTS:

POSITIVE

Article fulfill the requirements PN-EN 14465:2005, annex A. at the level category A

Attention: The test sample was acclimated according to PN-EN 20139:1993 (ISO 139)

Test operator

/M Sc. (Eng.) Jacek Komieczny/

PREZES ZARZĄDU


mgr inż. Piotr Błaczczak

TEST REPORT contain 1 page

The test results are only valid for the article tested.

This TEST REPORT shall not be reproduced, except in full, without the written approval of the laboratory.